

PRODUCT SPECIFICATIONCONFIDENTIALDocument No.BCY-PS-HA1-Rev620

<u>Date</u> 2010-05-07

<u>Rev</u> 6

PRODUCT SPECIFICATION

Rechargeable Lithium Ion Battery Model : ICR18650HA1 1300mAh

(For BMZ)



20 YOIDO-DONG YOUNGDUNGPO-GU, SEOUL 150-721, KOREA TEL : (82) 2-3773-1114 FAX : (82) 2-3773-7005

http://www.lgchem.com

LG Chem <u>Description</u> Lithium Ion ICR18650 HA1 1300mAh

PRODUCT SPECIFICATION

CONFIDENTIAL

Document No.DateBCY-PS-HA1-Rev62010-0

2010-05-07

Revision History

Revision	Date	Originator	Description
0	2006-12-27	Kim, Bong Tae	- Original Release
1	2007-03-30	Kim, Hong-Jeong	- Change of nominal capacity (1400 \rightarrow 1300 mAh)
2	2007-10-05	Kim, Hong-Jeong	- Separation of nominal capacity (Capacity for Standard and Fast charge/discharge)
3	2009-01-30	Kim, Sung Jong	- Cell dimension information was specified. (Standard of cell diameter = cell head)
4	2009-07-15	Kim, Sung Jong	Cell printing was changedMax charge voltage was added
5	2010-01-28	Choi, Yeong Gwang	- Change of Max. Discharge Current (18A \rightarrow 20A)
6	2010-05-07	Choi, Yeong Gwang	 Definitions of standard charge/discharge and fast charge/discharge were corrected. Measurement of recovery capacity was corrected.

LG Chem <u>Description</u> Lithium Ion ICR18650 HA1 1300mAh

PRODUCT SPECIFICATION

CONFIDENTIAL

Document No.	Date	Rev
BCY-PS-HA1-Rev6	2010-05-07	6

Contents

Contents
1. General Information4
1.1 Scope
1.2 Application
1.3 Product Classification
1.4 Model Name
2. Nominal Specification4
2.1 Capacity
2.2 Nominal Voltage
2.3.1 Standard Charge
2.3.2 Fast Charge
2.4 Max. Charge Voltage
2.5 Max. Charge Current
2.6.1 Standard Discharge
2.6.2 Fast Discharge
2.7 Weight
2.8 Operating Temperature
2.9 Storage Temperature (for shipping state)
3. Appearance and Dimension5
3.1 Appearance
3.2 Dimension
4. Performance Specification5
4.1 Standard Test Condition
4.2 Electrical Specification
4.3 Environmental Specification
4.4 Mechanical Specification
4.5 Safety Specification
5. Cautions and Prohibitions in Handling



Lithium Ion ICR18650 HA1 1300mAh

PRODUCT SPECIFICATION

CONFIDENTIAL

Document No.	Date	Rev
BCY-PS-HA1-Rev6	2010-05-07	6

1. General Information

1.1 Scope

This product specification defines the requirements of the rechargeable lithium ion battery to be supplied to the Customer by LG Chem.

- 1.2 Application: Power Tools
- 1.3 Product classification: Cylindrical rechargeable lithium ion battery
- 1.4 Model name: ICR18650HA1

2. Nominal Specification

Item	Condition / Note	Specification
2.1 Capacity	Std. charge / discharge	Nominal 1300 mAh (C _{nom})
		Minimum 1200 mAh (C _{min})
2.2 Nominal Voltage	Average for Std. discharge	3.68 V
2.3.1 Standard Charge	Constant current	650 mA
(Refer to 4.1.1)	Constant voltage	4.2 V
	End condition(Cut off)	50 mA
2.3.2 Fast charge	Constant current	4000 mA
(Refer to 4.1.3)	Constant voltage	4.2 V
	End condition(Cut off)	100 mA
2.4 Max. Charge Voltage	-	4.2 V
2.5 Max. Charge Current	-	4000 mA
2.6.1 Standard Discharge	Constant current	260 mA
(Refer to 4.1.2)	End voltage(Cut off)	2.5 V
2.6.2 Fast Discharge	Constant current	10000 mA
(Refer to 4.1.3)	End voltage(Cut off)	2.5 V
2.7 Max. Discharge Current	For continuous charge	15000 mA
2.8 Weight	Max.	46.0 g
2.9 Operating Temperature	Charge	0 ~ 45 ℃
	Discharge	-20 ~ 60 ℃
2.10 Storage Temperature	1 month	-20 ~ 60 °C
(for shipping state)	3 month	-20~45 ℃
	1 year	-20 ~ 20 °C

BCY-PS-HA1-Rev6

3. Appearance and Dimension

3.1 Appearance


There shall be no such defects as deep scratch, crack, rust, discoloration or leakage, which may adversely affect the commercial value of the cell.

3.2 Dimension

Diameter	-	18.3 + 0.1/-0.3 mm	$(M_{2} \times 18 / mm)$
Diametei	-	10.5 • 0.1/-0.5 11111	(wax. 10.4 mm)

Diameter is defined as the largest data value measured on the "A" area of a cylindrical cell.

Height : $65.0 \pm 0.2 \text{ mm}$ (Max. 65.2 mm)



4. Performance Specification

- 4.1 Standard test condition
 - 4.1.1 Standard Charge

Unless otherwise specified, "Standard Charge" shall consist of charging at constant current of 650 mA. The cell shall then be charged at constant voltage of 4.2 V while tapering the charge current. Charging shall be terminated when the charging current has tapered to 50 mA. For test purposes, charging shall be performed at $23 \pm 2^{\circ}$ C.

4.1.2 Standard Discharge

"Standard Discharge" shall consist of discharging at a constant current of 260 mA to 2.5 V. Discharging is to be performed at 23 ± 2 °C unless otherwise noted (such as capacity versus temperature).

4.1.3 Fast Charge / discharge condition

Cells shall be charged at constant current of 4000 mA to 4.2 V with end current of 100 mA. Cells shall be discharged at constant current of 10000 mA to 2.5 V. Cells are to rest 10 minutes after charge and 20 minutes after discharge.



Lithium Ion ICR18650 HA1 1300mAh

PRODUCT SPECIFICATION

CONFIDENTIAL

Document No.	Date	Rev
BCY-PS-HA1-Rev6	2010-05-07	6

4.2 Electrical Specification

Item	Condition	Specification
4.2.1	Cell shall be measured at 1kHz after charge per	\leq 30 m Ω , without PTC
Initial AC Impedance	4.1.1.	
4.2.2	Cells shall be charged per 4.1.1 and discharged	$C_{ini}~\geq~1200~mAh~(C_{min})$
Initial Capacity (C _{ini})	per 4.1.2 within 1h after full charge.	
4.2.3	Cells shall be charged and discharged per	$\geq~60~\%$ (of C_{min} in 2.1)
Cycle Life	4.1.3, 400 cycles. A cycle is defined as one	
	charge and one discharge. 401st discharge	
	capacity shall be measured per 4.1.1 and 4.1.2	

4.3 Environmental specification.

Item	Condition	Specification
4.3.1	Cells shall be charged per 4.1.1 and stored in a	Capacity remaining rate
Storage Characteristics	temperature-controlled environment at 23°C ±	$\geq~$ 90% of C_{ini}
	2°C for 30 days. After storage, cells shall be	
	discharged per 4.1.2 to obtain the remaining	
	capacity*.	
4.3.2	Cells shall be charged per 4.1.1 and stored in a	No leakage,
High Temperature	temperature-controlled environment at 60°C for	Capacity recovery rate \geq
Storage Test	1 week. After storage, cells shall be discharged	80% of Ci _{ni}
	per 4.1.2 and cycled per 4.1.1 and 4.1.2 for 3	
	cycles to obtain recovered capacity*.	
4.3.3	Cells are charged per 4.1.1 and stored at 60°C	No leakage, No rust
High Temperature and	(95% RH) for 168 hours. After test, cells are	Capacity recovery rate \geq
High Humidity Test	discharged per 4.1.2 and cycled per 4.1.1 and	80% of C _{ini}
	4.1.2 for 3 cycles to obtain recovered capacity.	
4.3.4	$65^{\circ}C$ (8h) \leftarrow 3hrs \rightarrow -20°C (8h) for 8 cycles	No leakage
Thermal Shock Test	with cells charged per 4.1.1 After test, cells are	Capacity recovery rate \geq
	discharged per 4.1.2 and cycled per 4.1.1 and	80% of C _{ini}
	4.1.2 for 3 cycles to obtain recovered capacity.	

^{*} Remaining Capacity : After storage, cells shall be discharged with standard condition(4.1.2) to measure the remaining capacity. ** Recovery Capacity : After storage, cells shall be discharged with standard discharge condition(4.1.2), and then cells shall be charged with standard charge condition(4.1.2), and then cells shall be repeated with standard discharge condition(4.1.2). This charge / discharge cycle shall be repeated three times to measure the recovery capacity.



PRODUCT SPECIFICATION

CONFIDENTIALDocument No.DateBCY-PS-HA1-Rev62010-05-076

Description	Ŭ		
Lithium Ion	ICR18650	HA1	1300mAh

4.3.5	Cells shall be c	Cells shall be charged per 4.1.1 at 23°C ± 2°C		
Temperature Dependency of	and discharged temperatures.	d per 4.1.2 at the followi	ng	
Capacity	Charge	Discharge	Capacity	
		-10 °C	60% of C _{ini}	
	23 °C	0°0	80% of C _{ini}	
	230	23 °C	100% of C _{ini}	
		0°0	95% of C _{ini}	

4.4 Mechanical Specification

Item	Condition	Specification
4.4.1	Cells charged per 4.1.1 are dropped onto an oak board	No leakage
Drop Test	from 1 meter height for 1 cycle, 2 drops from each cell	No temperature rising
	terminal and 1 drop from side of cell. (Total number of	
	drops =3).	
4.4.2	Cells charged per 4.1.1 are vibrated for 90 minutes per	No leakage
Vibration Test	each of the three mutually perpendicular axes (x, y, z)	
	with total excursion of 0.8mm, frequency of 10Hz to	
	55Hz and sweep of 1Hz change per minute.	

4.5 Safety Specification

Item	Condition	Specification
	Cells are discharged per 4.1.2, then charged at constant	
4.5.1	current of 3 times the max. charge condition and	No explode, No fire
Overcharge Test	constant voltage of 4.2V while tapering the charge	
	current. Charging is continued for 7 hours (Per UL1642).	
4.5.2	Cells are charged per 4.1.1, and the positive and	
External Short -	negative terminal is connected by a 100m $\ensuremath{\Omega}$ -wire for 1	No explode, No fire
Circuiting Test	hour (Per UL1642).	
4,5.3	Calle are discharged at constant surrent of 0.20 to	
Overdischarge	Cells are discharged at constant current of 0.2C to	No explode, No fire
Test	250% of the minimum capacity.	



Lithium Ion ICR18650 HA1 1300mAh

Description

PRODUCT SPECIFICATION

CONFIDENTIAL

 Document No.
 Date
 Rev

 BCY-PS-HA1-Rev6
 2010-05-07
 6

4.5.4 Heating Test	Cells are charged per 4.1.1 and heated in a circulating air oven at a rate of 5°C per minute to 130°C. At 130°C, oven is to remain for 10 minutes before test is discontinued (Per UL1642).	No explode, No fire
4.5.5 Impact Test	Cells charged per 4.1.1 are impacted with their longitudinal axis parallel to the flat surface and perpendicular to the longitudinal axis of the 15.8mm diameter bar (Per UL1642).	No explode, No fire
4.5.7 Crush Test	Cells charged per 4.1.1 are crushed with their longitudinal axis parallel to the flat surface of the crushing apparatus (Per UL1642).	No explode, No fire

5. Caution and Prohibition in Handling

Warning for using the lithium ion rechargeable battery. Mishandling of the battery may cause heat, fire and deterioration in performance. Be sure to observe the following.

Caution

- When using the application equipped with the battery, refer to the user's manual before usage.
- Please read the specific charger manual before charging.
- Charge time should not be longer than specified in the manual.
- When the cell is not charged after long exposure to the charger, discontinue charging.
- Battery must be charged at operating temperature range 0 ~ 45 ℃.
- Battery must be discharged at operating temperature range -20 ~ 60 °C.
- Please check the positive(+) and negative(-) direction before packing.
- When a lead plate or wire is connected to the cell for packing, check out insulation not to short-circuit.
- Battery must be stored separately.
- Battery must be stored in a dry area with low temperature for long-term storage.
- Do not place the battery in direct sunlight or heat.
- Do not use the battery in high static energy environment where the protection device can be damaged.
- When rust or smell is detected on first use, please return the product to the seller immediately.
- The battery must be away from children or pets
- When cell life span shortens after long usage, please exchange to new cells.

LG Chem <u>Description</u> Lithium Ion ICR18650 HA1 1300mAh **PRODUCT SPECIFICATION**

CONFIDENTIALDocument No.DateBCY-PS-HA1-Rev62010-05-07

Prohibitions

- Do not use different charger. Do not use cigarette jacks (in cars) for charging.
- Do not charge with constant current more than maximum charge current.
- Do not disassemble or reconstruct the battery.
- Do not throw or cause impact.
- Do not pierce a hole in the battery with sharp things. (such as nail, knife, pencil, drill)
- Do not use with other batteries or cells.
- Do not solder on battery directly.
- Do not press the battery with overload in manufacturing process, especially ultrasonic welding.
- Do not use old and new cells together for packing.
- Do not expose the battery to high heat. (such as fire)
- Do not put the battery into a microwave or high pressure container.
- Do not use the battery reversed.
- Do not connect positive(+) and negative(-) with conductive materials (such as metal, wire)
- Do not allow the battery to be immerged in or wetted with water or sea-water.