

<i>Prepared</i> LGCRP/BTC/BL	Park, Man Su	<i>Document No.</i> LRB-PS-I10C200-REVO	<i>Date</i> 2005-07-28	<i>Rev</i> 0
<i>Approved</i> LGCRP/BTC	Kim, Soo Ryoung	<i>Description</i> Lithium Ion ICP103450A1 2000mAh(Tentative)		




PRODUCT SPECIFICATION

Rechargeable Lithium Ion Battery

Model : ICP103450 A1 2000mAh (Tentative)

Revision History

REVISION	DATE	ORIGINATOR	REASON FOR CHANGE
0	2005-07-28	Park, Man Su	Original Release

Prepared	Reviewed	Approved
Park, Man Su  Date : 2005-07-28	Kim, Dong Myung  Date : 2005-07-28	Kim, Soo Ryoung  Date : 2005-07-28



Prepared		Document No.	Date	Rev
LGCRP/BTC/BL	Park, Man Su	LRB-PS-I10C200-REVO	2005-07-28	0
Approved		Description		
LGCRP/BTC	Kim, Soo Ryoung	Lithium Ion ICP103450A1 2000mAh(Tentative)		

1. Scope

This product specification defines the requirements of the rechargeable lithium ion battery to be supplied to the Customer by LG Chem, Ltd. Should there be any additional information required by the customer, customers are advised to contact LG Chem, Ltd before selecting a solution.

2. Description and Model

- | | |
|-----------------|------------------------------------|
| 2.1 Description | : Rechargeable Lithium Ion Battery |
| 2.2 Model | : ICP103450 A1 |

3. Technical Information

- | | | | | |
|-----|------------------------|-------------|---|---|
| 3.1 | Capacity | Nominal | : | 2050 mAh (by standard charge and discharge) |
| | | Minimum | : | 2000 mAh |
| 3.2 | Nominal Voltage | | : | Average 3.7V |
| 3.3 | Standard Charge | | : | Constant Current and Constant Voltage (CC/CV) |
| | | Current | = | 2000 mA |
| | | Voltage | = | 4.2 V |
| | | End Time | = | 2.5hours |
| 3.4 | Max. Charge Current | | : | 3000 mA |
| 3.5 | Standard Discharge | | : | Constant Current (CC) |
| | | Current | = | 400 mA |
| | | End Voltage | = | 2.75 V |
| 3.6 | Max. Discharge Current | | : | 4000 mA (for continuous discharge) |
| 3.7 | Weight | | : | Approx. 41.0g |
| 3.8 | Operating Temperature | Charge | : | 0 to 45 °C |
| | | Discharge | : | -20 to 60 °C |
| 3.9 | Storage Temperature | 1 month | : | -20 to 60 °C |
| | | 3 months | : | -20 to 45 °C |
| | | 1 year | : | -20 to 20 °C |

* Note : In case of Cycle Life test, Charge-Discharge current is according to 6.4

<i>Prepared</i> LGCRP/BTC/BL	Park, Man Su	<i>Document No.</i> LRB-PS-I10C200-REVO	<i>Date</i> 2005-07-28	<i>Rev</i> 0
<i>Approved</i> LGCRP/BTC	Kim, Soo Ryoung	<i>Description</i> Lithium Ion ICP103450A1 2000mAh(Tentative)		

4. Cell Dimensions

Thickness : Max. 11.4mm(at fully charged state)
 Width : 33.8 ± 0.15 mm
 Height : 49.4 ± 0.2 mm

5. Appearances

There shall be no such defects as deep scratch, crack, rust, discoloration or leakage, which may adversely affect the commercial value of the cell.

6. Characteristics

6.1 Standard Charge

Unless otherwise specified, "Standard Charge" shall consist of charging at constant current of 2000mA. The cell shall then be charged at constant voltage of 4.2V while tapering the charge current. Charging time is 2.5hours in all. For test purposes, charging shall be performed at $23^{\circ}\text{C} \pm 2^{\circ}\text{C}$.

6.2 Standard Discharge

"Standard Discharge" shall consist of discharging at a constant current of 400mA to 2.75V. Discharging is to be performed at $23^{\circ}\text{C} \pm 2^{\circ}\text{C}$ unless otherwise noted (such as capacity versus temperature).

6.3 Initial Capacity

Cells shall be charged per 6.1 and discharged per 6.2 within 1 hour after full charge. Initial capacity shall meet the following requirement.

$$\text{Initial Capacity} \geq 2000 \text{ mAh}$$

6.4 Cycle Life

Cells shall be charged at constant current of 2000mA to 4.2V with end current of 50mA. Cells shall be discharged at constant current of 2000mA to 3.0V. Cells are to rest 10 minutes after charge and 20 minutes after discharge. A cycle is defined as one charge and one discharge. Discharge capacity shall be measured per 6.1 and 6.2 after 300 cycles.

$$\text{Discharge capacity (301th Cycle)} \geq 80\% \text{ (of minimum capacity in 3.1)}$$



Prepared LGCRP/BTC/BL	Park, Man Su	Document No. LRB-PS-I10C200-REVO	Date 2005-07-28	Rev 0
Approved LGCRP/BTC	Kim, Soo Ryoung	Description Lithium Ion ICP103450A1 2000mAh(Tentative)		

6.5 Initial AC Impedance

Initial AC impedance is measured at 1kHz after standard charge.

$$\text{Initial AC Impedance} \leq 90 \text{ m}\Omega \text{ (with Thermal Fuse)}$$

6.6 Temperature Dependency of Capacity

Cells shall be charged per 6.1 at $23^{\circ}\text{C} \pm 2^{\circ}\text{C}$ and discharged per 6.2 at the following temperatures.

Relative capacity at each temperature shall meet the following.

Charge Temp.	Discharge Temperature			
23°C	-10°C	0°C	23°C	60°C
	70%	90%	100%	95%

6.7 Storage Characteristics

Cells shall be charged per 6.1 and stored in a temperature-controlled environment at $23^{\circ}\text{C} \pm 2^{\circ}\text{C}$ for 30 days. After storage, cells shall be discharged per 6.2 to obtain the remaining capacity.

$$\text{Remaining capacity} \geq 90\% \text{ (of minimum capacity in 3.1)}$$

6.8 Cell Voltage (as of shipment)

Voltage range : 3.7 ~ 3.9V

7. Mechanical Characteristics

7.1 Drop Test

Test method : Cells charged per 6.1 are dropped onto an oak board from 1.5 meter height for 3 cycles, where each cycle consists of 3 drops from each of the three mutually perpendicular axis (x, y, z) for total of 9 drops. After test, cells are discharged per 6.2 and cycled per 6.4 for 3 cycles to obtain recovered capacity.

Criteria : No leakage, Capacity recovery rate $\geq 80\%$

7.2 Vibration Test

Test method : Cells charged per 6.1 are vibrated for 90 minutes per each of the three mutually perpendicular axis (x, y, z) with total excursion of 0.8mm, frequency of 10Hz to 55Hz and sweep of 1Hz change per minute. After test, cells are discharged per 6.2 and cycled per 6.4 for 3 cycles to obtain recovered capacity.

Criteria : No leakage, Capacity recovery rate $\geq 80\%$



Prepared LGCRP/BTC/BL	Park, Man Su	Document No. LRB-PS-I10C200-REVO	Date 2005-07-28	Rev 0
Approved LGCRP/BTC	Kim, Soo Ryoung	Description Lithium Ion ICP103450A1 2000mAh(Tentative)		

8. Environmental Test

8.1 High Temperature Storage Test

Test method : Cells are charged per 6.1 and stored in a temperature-controlled environment at 60°C for 30 days. After test, cells are discharged per 6.2 and cycled per 6.4 for 3 cycles to obtain recovered capacity.

Criteria : No leakage, Capacity recovery rate \geq 70%

8.2 High Temperature and High Humidity Test

Test method : Cells are charged per 6.1 and stored at 60°C (95% RH) for 168 hours. After test, cells are discharged per 6.2 and cycled per 6.4 for 3 cycles to obtain recovered capacity.

Criteria : No leakage, No rust, Capacity recovery rate \geq 80%

8.3 Thermal Shock Test

Test method : 65°C (8Hrs) \leftarrow 3hrs \rightarrow -20°C (8Hrs) for 8 cycles with cells charged per 6.1. After test, cells are discharged per 6.2 and cycled per 6.4 for 3 cycles to obtain recovered capacity.

Criteria : No leakage, Capacity recovery rate \geq 80%

9. Safety Test

9.1 Overcharge test

Test method : Cells are discharged per 6.2, then charged at constant current of 9000mA and constant voltage of 4.2V while tapering the charge current. Charging is continued for 7 hours (Per UL1642).

Criteria : No rupture, No fire

9.2 External Short-circuiting Test

Test method : Cells are charged per 6.1, and the positive and negative terminal is connected by a 100m Ω -wire for 1 hour (Per UL1642).

Criteria : No rupture, No fire

9.3 Overdischarge Test

Test method : Cells are discharged at constant current of 400mA to 250% of the minimum capacity.

Criteria : No rupture, No fire



<i>Prepared</i> LGCRP/BTC/BL	Park, Man Su	<i>Document No.</i> LRB-PS-I10C200-REVO	<i>Date</i> 2005-07-28	<i>Rev</i> 0
<i>Approved</i> LGCRP/BTC	Kim, Soo Ryoung	<i>Description</i> Lithium Ion ICP103450A1 2000mAh(Tentative)		

9.4 Nail Test

Test method : A nail (diameter : 2.5~5mm) is penetrated vertically through the center of a fully charged cell and left for 6 hours.

Criteria : No rupture, No fire

9.5 Heating Test

Test method : Cells are charged per 6.1 and heated in a circulating air oven at a rate of 5°C per minute to 130°C. At 130°C, oven is to remain for 10 minutes before test is discontinued (Per UL1642).

Criteria : No rupture, No fire

9.6 Impact Test

Test method : Cells charged per 6.1 are impacted with their longitudinal axis parallel to the flat surface and perpendicular to the longitudinal axis of the 15.8mm diameter bar (Per UL1642).

Criteria : No rupture, No fire

9.7 Crush Test

Test method : Cells charged per 6.1 are crushed with their longitudinal axis parallel to the flat surface of the crushing apparatus (Per UL1642).

Criteria : No rupture, No fire

10. Standard Test Conditions

Unless otherwise specified, all tests stated in this Product Specification are conducted at temperature $23 \pm 2^{\circ}\text{C}$ and humidity $65 \pm 20\% \text{RH}$.

11. Product Liability

The coverage of LG Chem, Ltd. is for the cell itself, while the customer assumes the liability of the product including the cell and its protection circuit.

12. Others

Any matter not included in this specification shall be conferred between the both parties.

This document shall replace the document bearing a former revision index, and customers are kindly requested to destroy the former document in possession.



<i>Prepared</i> LGCRP/BTC/BL	Park, Man Su	<i>Document No.</i> LRB-PS-I10C200-REV0	<i>Date</i> 2005-07-28	<i>Rev</i> 0
<i>Approved</i> LGCRP/BTC	Kim, Soo Ryoung	<i>Description</i> Lithium Ion ICP103450A1 2000mAh(Tentative)		

Fig 1. Dimensional Drawing of ICP103450 A1

